BLOQ

creative
carpet tiles



THE BINARY

BALANCE

SPECIFICATIONS

TYPE OF MANUFACTURE ISO 2424	Tufted Patterned Loop Pile 1/10”
PILE FIBER COMPOSITION ISO 2424	100% Polyamide 6 Solution Dyed Nylon made by Aquafil
SECONDARY BACKING ISO 2424	Bitback, Modified Bitumen 70% Recycled Content
DIMENSION EN ISO 24342	50 x 50 cm
PILE WEIGHT ISO 8543	650 g/m²
SURFACE PILE WEIGHT ISO 8543	380 g/m²
TOTAL WEIGHT ISO 8543	4 400 g/m²
TOTAL THICKNESS ISO 1765	6.9 mm
PILE HEIGHT ISO 1766	3.8 mm
PILE DENSITY ISO 8543	0.100 g/m³
NUMBER OF TUFTS ISO 1763	152 000 /m²
DIMENSIONAL STABILITY ISO 2551	≤ 0.2%
NUMBER OF COLOURS	18
PACKAGING	Box: 20 tiles / 5 m² Pallet: 200 m²

PERFORMANCE

CLASSIFICATION EN 1307	33
LUXURY RATING EN 1307	LC1
CASTOR CHAIR RATING EN 985	A: Intensive use
FIRE CLASSIFICATION EN 13501-1	B_{fl}-s1
IMPACT SOUND INSULATION EN ISO 10140-3	ΔL_w: 26 dB
SOUND ABSORBTION EN ISO 354	Frequency Hz 125 250 500 1000 2000 4000 α_s 0.00 0.03 0.08 0.19 0.34 0.38
NOISE REDUCTION EN ISO 354	α_w: 0.20
PERMANENT ANTISTATIC ISO 6356	≤ 2 kV
TRANSVERSAL RESISTANCE ISO 10965	≤ 1 X 10^9 Ohm
THERMAL RESISTANCE ISO 8302	0.079 m² K/W
COLOUR FASTNESS TO LIGHT EN ISO 105-B02	≥ 7
COLOUR FASTNESS TO WATER EN ISO 105-E01	≥ 4
RUBBING FASTNESS EN ISO 105-X12	≥ 4
GUT N° PRODIS	F42D2D9F

Made in the Netherlands (EU)

ÉMISSIONS DANS L'AIR INTÉRIEUR* A+

synthetic fibres and polymers

EN 14041
DOP: 1137-127659
NB: 2401
20
For use as floor covering in buildings.
BLOQ
De Blokmat 29
NL - 8281 JH Genemuiden

BSI 14041
DOP: 1137-127659-UK
AB: 2401
20
FOR USE AS FLOOR COVERING IN BUILDINGS.
BLOQ
De Blokmat 29
NL - 8281 JH Genemuiden

02/06/2022

All rights reserved to alter technical specifications.