


BLOQ

creative
carpet tiles




THE WORKPLACE TRADITION

SPECIFICATIONS

TYPE OF MANUFACTURE	Tufted Loop Pile 1/10"
	ISO 2424
PILE FIBER COMPOSITION	100% Polyamide 6
	ISO 2424 Solution Dyed Nylon made by Aquafil
SECONDARY BACKING	Bitback, Modified Bitumen
	ISO 2424 70% Recycled Content
DIMENSION	50 x 50 cm
	EN ISO 24342
PILE WEIGHT	540 g/m ²
	ISO 8543
SURFACE PILE WEIGHT	380 g/m ²
	ISO 8543
TOTAL WEIGHT	4 250 g/m ²
	ISO 8543
TOTAL THICKNESS	6.0 mm
	ISO 1765
PILE HEIGHT	2.7 mm
	ISO 1766
PILE DENSITY	0.139 g/m ³
	ISO 8543
NUMBER OF TUFTS	156 000 /m ²
	ISO 1763
DIMENSIONAL STABILITY	≤ 0.2%
	ISO 2551
NUMBER OF COLOURS	30
PACKAGING	Box: 20 tiles / 5 m ² Pallet: 200 m ²

PERFORMANCE

CLASSIFICATION	33
	EN 1307
LUXURY RATING	LC1
	EN 1307
CASTOR CHAIR RATING	A: Intensive use
	EN 985
FIRE CLASSIFICATION	B _{fl} -s1
	EN 13501-1
IMPACT SOUND INSULATION	ΔL _w : 24 dB
	EN ISO 10140-3
SOUND ABSORPTION	Frequency Hz 125 250 500 1000 2000 4000
	EN ISO 354 α _s 0.00 0.03 0.07 0.19 0.30 0.35
NOISE REDUCTION	α _w : 0.15
	EN ISO 354
PERMANENT ANTISTATIC	≤ 2 kV
	ISO 6356
TRANSVERSAL RESISTANCE	≤ 1 X 10 ⁹ Ohm
	ISO 10965
THERMAL RESISTANCE	0.064 m ² K/W
	ISO 8302
COLOUR FASTNESS TO LIGHT	≥ 7
	EN ISO 105-B02
COLOUR FASTNESS TO WATER	≥ 4
	EN ISO 105-E01
RUBBING FASTNESS	≥ 4
	EN ISO 105-X12
GUT N° PRODIS	23304A8C



Made in the Netherlands (EU)

EMISSIONS DANS L'AIR INTERIEUR: A+

AQUAFIL synthetic fibres and polymers

EN 14041
DOP: 1137-127686
NB: 2401
20
CE
Bfl-s1 DS PCP NA HCHO
λ23 λ23
For use as floor covering in buildings.
BLOQ
De Blokmat 29
NL - 8281 JH Genemuiden

BSI 14041
DOP: 1137-127686-UK
AB: 2401
20
UK CA
Bfl-s1 NCS PCP DL
NA HCHO λ23 λ23
FOR USE AS FLOOR COVERING IN BUILDINGS.
BLOQ
De Blokmat 29
NL - 8281 JH Genemuiden

All rights reserved to alter technical specifications.